



Prod. Ref.	12661-000
Safety cat.	S2 SRC
Range of sizes	36 - 47 (3 - 12)
Weight (sz. 8)	515 g
Shape	A
Width (3 - 6)	10
Width (6,5 - 12)	11

Description: White water repellent **ECOLORICA**[®] shoe, **DRYFRESH** 100% polyester fabric lining, antistatic, anti-shock, slipping resistant

Plus: 100% METAL FREE. The upper is easy to clean, up to 40°C, with neutral soap and water, keeping intact its aesthetic and tactile features. **EVANIT** footbed, made of EVA and nitrile special compound, with high bearing capacity and variable thickness. Thermoformed, anatomic, punched and coated with highly breathable fabric. Antistatic thanks to a specific treatment on the surface and to seams made of conductive yarns. **ANTI TORSION SUPPORT** made of polycarbonate and fibreglass conveniently placed between heel and sole, which provides support and protection of the plantar arch, thus preventing harmful bendings and/or unwilling torsion. Perfumed sole

Suggested uses: Footwear for chemical industry and food industry. Footwear for hospital service

Care and maintenance: Clean after each use and dry off away from direct heat. Avoid contact with aggressive chemicals or extreme temperature. Avoid immersion in sea water, lime water or cement mixed with water

MATERIALS / ACCESSORIES

SAFETY TECHNICAL SPECIFICATIONS

		Clause EN ISO 20345:2011	Description	Unit	Cofra result	Requirement
Complete shoe	Toe cap: non metallic TOP RETURN toe cap, impact resistant until 200 J and compression resistant until 1500 kg	5.3.2.3	Shock resistance (clearance after shock)	mm	15,5	≥ 14
		5.3.2.4	Compression resistance (clearance after compression)	mm	15	≥ 14
	Antistatic shoe: the bottom is fit for the dissipation of electrostatic charges	6.2.2.2	Electric resistance - wet - dry	MΩ MΩ	13,3 461	≥ 0.1 ≤ 1000
	Energy absorption system	6.2.4	Shock absorption	J	34	≥ 20
Upper	White water repellent ECOLORICA [®] thickness 1,6 mm	5.4.6	Water vapour permeability Permeability coefficient	mg/cmq h mg/cmq	> 1,5 > 15,8	≥ 0,8 > 15
		6.3.1	Water absorption Water penetration		20% 0,0 g	≤ 30% ≤ 0,2 g
		5.5.3	Water vapour permeability Permeability coefficient	mg/cmq h mg/cmq	> 6,3 > 51,1	≥ 2 ≥ 20
Vamp lining	Textile, breathable, abrasion resistant, colour white Thickness 1,2 mm	5.5.3	Water vapour permeability Permeability coefficient	mg/cmq h mg/cmq	> 9,9 > 80	≥ 2 ≥ 20
Quarter lining	DRYFRESH 100% polyester fabric, breathable, abrasion resistant, colour white thickness 1,2 mm	5.5.3	Water vapour permeability Permeability coefficient	mg/cmq h mg/cmq	> 9,9 > 80	≥ 2 ≥ 20
Insole	Antistatic, absorbent, abrasion and flaking resistant	5.7.4.1	Abrasion resistance	cycle	> 400	≥ 400
Sole	Antistatic Polyurethane/TPU directly injected in the upper: Outsole: White TPU, slipping resistant, abrasion resistant and hydrocarbons resistant. Midsole: White polyurethane, low density, comfortable and anti-shock.	5.8.3	Abrasion resistance (lost volume)	mm ³	66	≤ 150
		5.8.4	Flexing resistance (cut increase)	mm	2	≤ 4
		5.8.6	Interlayer bond strength	N/mm	3,8	≥ 3
		6.4.2	Hydrocarbons resistance (ΔV = volume increase)	%	1	≤ 12
		5.3.5	SRA : ceramic + detergent solution – flat SRA : ceramic + detergent solution – heel (contact angle 7°) SRB : steel + glycerol – flat SRB : steel + glycerol – heel (contact angle 7°)			0,40 0,31 0,19 0,16
	Adherence coefficient of the sole	5.3.5				